

# Two-Component Aliphatic Polyurea Topcoat, Fast- or Moderate-Drying, Performance-Based

# Two-Component Aliphatic Polyurea Topcoat, Fast- or Moderate-Drying, Performance-Based

This AMPP standard represents a consensus of those individual members who have reviewed this document, its scope, and provisions. Its acceptance does not in any respect preclude anyone, whether he or she has adopted the standard or not, from manufacturing, marketing purchasing, or using products, processes, or procedures not in conformance with this standard. Nothing contained in this AMPP standard is to be construed as granting any right, by implication or otherwise, to manufacture, sell, or use in connection with any method, apparatus, or product covered by Letters Patent, or as indemnifying or protection anyone against liability for infringement of Letters Patent. This standard represents minimum requirements and should in no way be interpreted as a restriction on the use of better procedures or materials. Neither is this standard intended to apply in all cases relating to the subject. Unpredictable circumstances may negate the usefulness of this standard in specific instances. AMPP assumes no responsibility for the interpretation or use of this standard by other parties and accepts responsibility for only those official AMPP interpretations issued by AMPP in accordance with its governing procedures and policies which preclude the issuance of interpretations by individual volunteers.

Users of this AMPP standard are responsible for reviewing appropriate health, safety, environmental, and regulatory documents and for determining their applicability in relation to this standard prior to its use. This AMPP standard may not necessarily address all potential health and safety problems, or environmental hazards associated with the use of materials, equipment, and/or operations detailed or referred to within this standard. Users of this AMPP standard are also responsible for establishing appropriate health, safety, and environmental protection practices, in consultation with appropriate regulatory authorities, if necessary, to achieve compliance with any existing applicable regulatory requirements prior to the use of this standard.

CAUTIONARY NOTICE: AMPP standards are subject to periodic review and may be revised or withdrawn at any time in accordance with AMPP technical committee procedures. AMPP requires that action be taken to reaffirm, revise, or withdraw this standard no later than five years from the date of initial publication and subsequently from the date of each reaffirmation or revision. The user is cautioned to obtain the latest edition. Purchasers of AMPP standards may receive current information on all standards and other AMPP/NACE/SSPC publications by contacting AMPP Customer Support, 15835 Park Ten Place, Houston, Texas 77084-5145 (Tel: [+1-281-228-6200](tel:+1-281-228-6200), email: [customersupport@ampp.org](mailto:customersupport@ampp.org)).

## Document History:

2023-05-09: Reaffirmed by AMPP Standards Committee (SC) 02, Exterior Coatings–Atmospheric

2015-04-23: Revised by SSPC C.1.9, Polyurea Coatings

2004-04-01: Approved by SSPC C.1.9, Polyurea Coatings

AMPP values your input. To provide feedback on this standard, please contact: [standards@ampp.org](mailto:standards@ampp.org)

## SSPC-Paint 39-2023

©2023 Association for Materials Protection and Performance (AMPP). All rights reserved.

# Two-Component Aliphatic Polyurea Topcoat, Fast- or Moderate-Drying, Performance-Based

Section 1	Scope.....	4
Section 2	Description.....	4
Section 3	Referenced Standards and Other Consensus Documents.....	4
Section 4	Composition Requirements.....	5
Section 5	Requirements of Liquid Coating.....	6
Section 6	Test Panel Preparation.....	6
Section 7	Weathering Requirements.....	6
Section 8	Laboratory Physical Tests of Applied Coatings.....	7
Section 9	Material Quality Assurance.....	9
Section 10	Labeling.....	9
Appendix A	Notes (Nonmandatory).....	9
Tables		
Table 1	Summary of Performance Testing Results to be Reported.....	6
Table 2	Physical Performance Test Results.....	8

In AMPP standards, the terms *shall* and *must* are used to state requirements and are considered mandatory. The term *should* is used to state something that is recommended, but is not considered mandatory. The term *may* is used to state something considered optional

## Section 1: Scope

- 1.1 This specification contains performance requirements for a two-component, weatherable polyurea topcoat. The coating may be fast or moderately fast drying (see [Paragraph A1 of nonmandatory Appendix A](#)).
- 1.2 Coatings meeting the requirements of this specification are generally suitable for exposures in Environmental Zones 1A (interior, normally dry) 1B (exterior, normally dry), 2A (frequently wet by fresh water, excluding immersion), and 2B (frequently wet by salt water, excluding immersion). Resistance of polyurea topcoats in Environmental Zones 3B (chemical exposure, neutral) and 3C (chemical exposure, alkaline) will vary based upon formulation. The coating manufacturer should be contacted for specific chemical resistance data if required.
- 1.3 The specified coating is intended for application by brush, spray roller, or plural-component equipment, depending upon its formulation. It is generally applied over a primer or intermediate coat.
- 1.4 This coating is intended for use as a topcoat over ferrous metal and cementitious substrates that have been suitably primed.

## Section 2: Description

- 2.1 The resins used in the coating result in a polyurea product as described in [Paragraph A1](#) or a hybrid system as described in [Paragraph A2](#).
- 2.2 Coating Type: The two types of polyurea coatings are differentiated by drying time.
  - 2.2.1 Type 1 (Fast Drying): A Type 1 coating dries to handle in less than 30 minutes (per ASTM D1640).
  - 2.2.2 Type 2 (Moderate Drying): A Type 2 coating dries to handle from 30 minutes to two hours (per ASTM D1640).

## Section 3: Referenced Standards and Other Consensus Documents

- 3.1 The latest issue, revision, or amendment of the referenced standards in effect on the date of invitation to bid shall govern, unless otherwise specified. Standards marked with an asterisk (\*) are referenced only in the Notes of nonmandatory Appendix A, and are not requirements of this standard.
- 3.2 If there is a conflict between the requirements of any of the cited referenced standards and this specification, the requirements of this specification shall prevail.