

Post-Installed Adhesive Anchors in Concrete— Qualification Requirements and Commentary

Reported by ACI Committee 355

ACI CODE-355.4-24



American Concrete Institute
Always advancing



Post-Installed Adhesive Anchors in Concrete—Qualification Requirements and Commentary

Copyright by the American Concrete Institute, Farmington Hills, MI. All rights reserved. This material may not be reproduced or copied, in whole or part, in any printed, mechanical, electronic, film, or other distribution and storage media, without the written consent of ACI.

The technical committees responsible for ACI committee reports and standards strive to avoid ambiguities, omissions, and errors in these documents. Despite these efforts, the users of ACI documents occasionally find information or requirements that may be subject to more than one interpretation or may be incomplete or incorrect. Users who have suggestions for the improvement of ACI documents are requested to contact ACI via the errata website at <http://concrete.org/Publications/DocumentErrata.aspx>. Proper use of this document includes periodically checking for errata for the most up-to-date revisions.

ACI committee documents are intended for the use of individuals who are competent to evaluate the significance and limitations of its content and recommendations and who will accept responsibility for the application of the material it contains. Individuals who use this publication in any way assume all risk and accept total responsibility for the application and use of this information.

All information in this publication is provided “as is” without warranty of any kind, either express or implied, including but not limited to, the implied warranties of merchantability, fitness for a particular purpose or non-infringement.

ACI and its members disclaim liability for damages of any kind, including any special, indirect, incidental, or consequential damages, including without limitation, lost revenues or lost profits, which may result from the use of this publication.

It is the responsibility of the user of this document to establish health and safety practices appropriate to the specific circumstances involved with its use. ACI does not make any representations regarding health and safety issues and the use of this document. The user must determine the applicability of all regulatory limitations before applying the document and must comply with all applicable laws and regulations, including but not limited to, United States Occupational Safety and Health Administration (OSHA) health and safety standards.

Participation by governmental representatives in the work of the American Concrete Institute and in the development of Institute standards does not constitute governmental endorsement of ACI or the standards that it develops.

ACI documents are written via a consensus-based process. The characteristics of ACI technical committee operations include:

- (a) Open committee membership
- (b) Balance/lack of dominance
- (c) Coordination and harmonization of information
- (d) Transparency of committee activities to public
- (e) Consideration of views and objections
- (f) Resolution through consensus process

The technical committee documents of the American Concrete Institute represent the consensus of the committee and ACI. Technical committee members are individuals who volunteer their services to ACI and specific technical committees.

American Concrete Institute
38800 Country Club Drive
Farmington Hills, MI 48331
Phone: +1.248.848.3700
Fax: +1.248.848.3701

Post-Installed Adhesive Anchors in Concrete— Qualification Requirements and Commentary

An ACI Standard

Reported by ACI Committee 355

Andra Hoermann-Gast, Chair

Jay Dorst, Vice Chair

John F. Silva, Vice Chair

Neal S. Anderson
Jacques A. Bertrand
T.J. Bland
Rachel Chicchi Cross
Rolf Eligehausen
Werner A. F. Fuchs

Brian C. Gerber
Jan Erich Hofmann
Chiwan Wayne Hsieh
Amy S. Kolczak
Thomas A. Kolden
Anthony J. Lamanna

Giovanni Muciaccia
Daniel T. Mullins
John E. Pearson
Marlou B. Rodriguez
Milton Rodriguez
Peter C. Schillinger

Howard Silverman
Luke Tavernit
Jason H. Wagner
Roman Wan-Wendner

Consulting Members

Peter J. Carrato
Ronald A. Cook
Branko Galunic

Neil M. Hawkins
Christopher La Vine
Nam-Ho Lee

Lee W. Mattis
Robert R. McGlohn
Donald F. Meinheit

Conrad Paulson
Dan R. Stoppenhagen

This Code prescribes testing programs and evaluation requirements for post-installed adhesive anchors intended for use in concrete under the design provisions of ACI CODE-318-25. Testing and assessment criteria are provided for various conditions of use, including seismic loading; sustained loading; aggressive environments; reduced and elevated temperatures; and for determining whether anchors are acceptable for use in uncracked concrete only, or acceptable for service both in cracked and uncracked concrete. Criteria are provided for establishing the characteristic bond strength, reductions for adverse conditions, and the anchor category and associated jobsite quality control requirements.

Keywords: adhesive anchors; cracked concrete; fasteners; post-installed anchors; qualification procedures; uncracked concrete.

CONTENTS

CHAPTER 1—INTRODUCTION, p. 4

- 1.1—Introduction, p. 4
- 1.2—Scope, p. 4
- 1.3—Units of measurement, p. 7

CHAPTER 2—NOTATION AND DEFINITIONS, p. 8

- 2.1—Notation, p. 8
- 2.2—Definitions, p. 13

CHAPTER 3—GENERAL REQUIREMENTS, p. 19

- 3.1—Test organization, p. 19
- 3.2—Variables and options, p. 19

ACI CODE-355.4-24 supersedes ACI 355.4-19(21) and was approved by the ACI Standards Board for publication August 2024, and published November 2024. This Code was first published in 2011 and revised in 2019.

Copyright © 2024, American Concrete Institute.

All rights reserved including rights of reproduction and use in any form or by any means, including the making of copies by any photo process, or by electronic or mechanical device, printed, written, or oral, or recording for sound or visual reproduction or for use in any knowledge or retrieval system or device, unless permission in writing is obtained from the copyright proprietors.

- 3.3—Required tests for qualification, p. 20
- 3.4—Assessment for multiple anchor element types for adhesive anchors, p. 27
- 3.5—Assessment for alternative drilling methods, p. 28

CHAPTER 4—REQUIREMENTS FOR TEST SPECIMENS, ANCHOR INSTALLATION, AND TESTING, p. 30

- 4.1—Testing by ITEA and manufacturer, p. 30
- 4.2—Test samples, p. 30
- 4.3—Concrete for test members, p. 31
- 4.4—Requirements for test members, p. 32
- 4.5—Anchor installation, p. 38
- 4.6—Drill bit requirements, p. 40
- 4.7—Test methods, p. 40
- 4.8—Tests in cracked concrete, p. 45
- 4.9—Seismic tests, p. 46
- 4.10—Changes to products, p. 48

CHAPTER 5—REQUIREMENTS FOR ANCHOR IDENTIFICATION, p. 49

- 5.1—Basic requirements, p. 49
- 5.2—Verification, p. 49
- 5.3—Fingerprinting adhesive materials, p. 49
- 5.4—Packaging, p. 49

CHAPTER 6—REFERENCE TESTS, p. 50

- 6.1—Purpose, p. 50
- 6.2—Required tests, p. 50
- 6.3—Conduct of tests, p. 51

CHAPTER 7—RELIABILITY TESTS, p. 52

- 7.1—Purpose, p. 52
- 7.2—Required tests, p. 52
- 7.3—Conduct of tests, p. 52
- 7.4—Reliability tests, p. 52
- 7.5—Sensitivity to hole cleaning: dry concrete, p. 53
- 7.6—Sensitivity to hole cleaning: saturated concrete, p. 53
- 7.7—Sensitivity to hole cleaning: water-filled hole, p. 54
- 7.8—Sensitivity to hole cleaning: submerged concrete, p. 55
- 7.9—Sensitivity to mixing effort, p. 55
- 7.10—Sensitivity to installation in water-saturated concrete, p. 56
- 7.11—Sensitivity to installation in water-filled hole: saturated concrete, p. 56
- 7.12—Sensitivity to installation in submerged concrete, p. 56
- 7.13—Sensitivity to crack width—low-strength concrete, p. 56
- 7.14—Sensitivity to crack width: high-strength concrete, p. 56
- 7.15—Sensitivity to crack width cycling, p. 57
- 7.16—Sensitivity to freezing and thawing, p. 59
- 7.17—Sensitivity to sustained loading at standard and maximum long-term temperature, p. 60
- 7.18—Sensitivity to installation direction, p. 63
- 7.19—Torque test, p. 64

CHAPTER 8—SERVICE-CONDITION TESTS, p. 65

- 8.1—Purpose, p. 65
- 8.2—Required tests, p. 65
- 8.3—Conduct of tests, p. 65
- 8.4—Tension tests in uncracked and cracked concrete, p. 65
- 8.5—Tension tests at elevated temperature, p. 65
- 8.6—Tension tests with decreased installation temperature, p. 66
- 8.7—Establishment of cure time at standard, minimum, and maximum temperature, p. 69
- 8.8—Durability assessment, p. 69
- 8.9—Verification of full concrete capacity in a corner, p. 71
- 8.10—Determination of minimum spacing and edge distance to preclude splitting, p. 71
- 8.11—Tests to determine shear capacity of anchor elements with nonuniform cross section, p. 72
- 8.12—Seismic cyclic tension tests, p. 73
- 8.13—Seismic cyclic shear tests, p. 75
- 8.14—Seismic crack cycling tests, p. 77

CHAPTER 9—SUPPLEMENTAL TEST, p. 81

- 9.1—Round-robin tests, p. 81
- 9.2—Tests to determine minimum member thickness, p. 82
- 9.3—Tests for recognition of deformed reinforcing bars as anchor elements, p. 83
- 9.4—Tests for supplementary recognition of metric threaded rods as anchor elements, p. 84
- 9.5—Tests for supplementary recognition of fractional threaded rods as anchor elements, p. 85

CHAPTER 10—ASSESSMENT OF ANCHORS, p. 87

- 10.1—Analysis of data, p. 87
- 10.2—Normalization of anchor capacities for measured concrete bond and steel strengths, p. 87
- 10.3—Establishing characteristic values, p. 88
- 10.4—Assessment of characteristic tension capacity associated with concrete breakout and pullout, p. 88
- 10.5—Assessment of steel tension capacity, p. 98
- 10.6—Assessment of steel shear capacity (8.11), p. 98
- 10.7—Assessment of minimum member thickness (9.2), p. 99
- 10.8—Assessment of maximum tightening torque (7.19), p. 99
- 10.9—Assessment of behavior under crack cycling (7.15), p. 100
- 10.10—Assessment of freezing-and-thawing behavior (7.16), p. 100
- 10.11—Assessment of sustained load behavior (7.17), p. 100
- 10.12—Assessment of performance associated with installation direction (7.18), p. 102
- 10.13—Assessment of performance at elevated temperature (8.5), p. 103

- 10.14—Assessment of performance with decreased installation temperature (8.6), p. 103
- 10.15—Assessment for establishment of cure time at standard temperature (8.7), p. 104
- 10.16—Assessment of durability requirement (8.8), p. 105
- 10.17—Assessment of performance in corner test (8.9), p. 105
- 10.18—Assessment of performance in minimum spacing and edge distance test (8.10), p. 105
- 10.19—Assessment of seismic tests (8.12, 8.13, 8.14), p. 106
- 10.20—Determination of seismic characteristic strength, p. 117
- 10.21—Establishment of hole-cleaning procedures, p. 118
- 10.22—Establishment of on-site quality control and installation conditions, p. 118
- 10.23—Assessment based on installation and environmental conditions, p. 119
- 10.24—Assessment for fire exposure, p. 119

CHAPTER 11—DATA PRESENTATION, p. 120

- 11.1—General requirements, p. 120
- 11.2—Contents of the evaluation report, p. 120
- 11.3—Data presentation, p. 120

CHAPTER 12—INDEPENDENT TESTING AND EVALUATION AGENCY REQUIREMENTS, p. 123

- 12.1—General requirements, p. 123
- 12.2—Certification, p. 123

CHAPTER 13—QUALITY CONTROL REQUIREMENTS, p. 124

- 13.1—Quality assurance program, p. 124
- 13.2—Quality control manuals, p. 124
- 13.3—Special inspection, p. 124

CHAPTER 14—REFERENCES, p. 126

- Authored references, p. 126



CODE

CHAPTER 1—INTRODUCTION

1.1—Introduction

This Code prescribes testing and evaluation requirements for post-installed adhesive anchor systems intended for use in concrete under the provisions of **ACI CODE-318**. Criteria are separately prescribed to determine the suitability of adhesive anchors used in uncracked concrete only, or in both cracked and uncracked concrete. Criteria are prescribed to determine the design parameters and performance category for adhesive anchors. Included are assessments of the adhesive anchor system for bond strength, reliability, service conditions, and quality control. Special inspection (**13.3**) is required during anchor installation as noted in **10.22**. Table 1.1 provides an overview of the scope.

Table 1.1—Overview of anchor system

Anchor type	Embedded part	Assessment criteria	
Adhesive anchor	Threaded rods, deformed reinforcing bars, or internally threaded steel sleeves with external deformations	Uncracked concrete	Table 3.3.1
		Cracked and uncracked concrete	Table 3.3.2a or Table 3.3.2b

1.2—Scope

This Code applies only to post-installed adhesive anchors as defined herein.

1.2.1 This Code applies to anchors with a diameter d_a of 1/4 in. or larger. The drilled hole shall be approximately cylindrical with a diameter $d_o \leq 1.5d_a$. This Code also applies to anchors with an anchor embedment depth h_{ef} not less than four diameters ($4d_a$), or 1-5/8 in., and an embedment depth not exceeding $20d_a$.

COMMENTARY

CHAPTER R1—INTRODUCTION

R1.1—Introduction

This Code prescribes the testing programs required to qualify post-installed adhesive anchor systems for design in accordance with ACI CODE-318 Chapter 17. ACI CODE-318 Chapter 17 requires that anchors be tested either for use exclusively in uncracked concrete or for use in cracked and uncracked concrete conditions, whereby it is understood that the presence of cracking may occur at any time over the service life of the anchors. Test and assessment criteria are provided for various conditions, including loads (seismic and sustained), environmental with regard to humidity and temperature, and determination if anchors are acceptable for use in cracked or uncracked concrete. Refer to **Cook and Konz (2001)** for a review of factors that influence adhesive anchor behavior. Refer to **Fuchs et al. (1995)** for background on the concrete breakout design model and to **Eligehausen et al. (2006)** and **Zamora et al. (2003)** for a discussion of bond models for adhesive and grouted anchors. For a discussion of issues associated with the qualification and design of systems for post-installed reinforcing bars, refer to **Spiehl et al. (2001)**. For background on seismic testing and assessment of anchors, refer to **Hoehler and Eligehausen (2008)**, **Hoehler et al. (2011)**, and **Mahrenholtz et al. (2016, 2017)**.

R1.2—Scope

Adhesive anchors resist tension loads with a combination of adhesion and mechanical bond (micro-interlock). Different anchor designs and adhesive types may exhibit a range of performance characteristics. In particular, the sensitivity of adhesive anchors to variations in installation and service-condition parameters (such as hole cleaning, installation orientation, and cracked concrete characteristics) may vary widely from each system. ACI CODE-318 addresses this situation by matching capacity reduction factors to anchor performance categories that are, in turn, established through a series of reliability tests.

R1.2.1 The minimum diameter of 1/4 in. is based on practical considerations regarding the limit of structural anchor applications. The upper limit on the ratio of hole diameter to anchor element diameter provides a demarcation between conditions where a single bond strength can be used to evaluate anchor strength and conditions where bond strengths at both the anchor interface and concrete interface must be determined to evaluate anchor strength. In addition, the value of $1.5d_a$ is based on consideration of typical practice whereby most organic adhesives are used with thin bond lines to limit both adhesive shrinkage and creep of the anchor