

ASCE STANDARD

ASCE/SEI

**8-22**

# Specification for the Design of Cold-Formed Stainless Steel Structural Members

ASCE STANDARD

ASCE/SEI

**8-22**

# **Specification for the Design of Cold-Formed Stainless Steel Structural Members**



PUBLISHED BY THE AMERICAN SOCIETY OF CIVIL ENGINEERS

## Library of Congress Cataloging-in-Publication Data

Names: American Society of Civil Engineers, author.

Title: Specification for the design of cold-formed stainless steel structural members / American Society of Civil Engineers.

Description: Reston, Virginia : American Society of Civil Engineers, [2023] | Includes bibliographical references and index. | Summary: "Specification for the Design of Cold-Formed Stainless Steel Structural Members, ASCE/SEI 8-22 provides design criteria for stainless steel structural members and connections in buildings and other statically loaded structures"— Provided by publisher.

Identifiers: LCCN 2021043108 | ISBN 9780784415955 (soft cover) | ISBN 9780784483831 (pdf)

Subjects: LCSH: Building, Iron and steel—Standards—United States. | Steel, Structural—Standards—United States. | Stainless steel—Standards—United States. | Load factor design.

Classification: LCC TA684 .A49 2022 | DDC 691/.7—dc23/eng/20211028

LC record available at <https://lcn.loc.gov/2021043108>

Published by American Society of Civil Engineers

1801 Alexander Bell Drive

Reston, Virginia, 20191-4382

[www.asce.org/bookstore](http://www.asce.org/bookstore) | [ascelibrary.org](http://ascelibrary.org)

This standard was developed by a consensus standards development process that has been accredited by the American National Standards Institute (ANSI). Accreditation by ANSI, a voluntary accreditation body representing public and private sector standards development organizations in the United States and abroad, signifies that the standards development process used by ASCE has met the ANSI requirements for openness, balance, consensus, and due process.

While ASCE's process is designed to promote standards that reflect a fair and reasoned consensus among all interested participants, while preserving the public health, safety, and welfare that is paramount to its mission, it has not made an independent assessment of and does not warrant the accuracy, completeness, suitability, or utility of any information, apparatus, product, or process discussed herein. ASCE does not intend, nor should anyone interpret, ASCE's standards to replace the sound judgment of a competent professional, having knowledge and experience in the appropriate field(s) of practice, nor to substitute for the standard of care required of such professionals in interpreting and applying the contents of this standard.

ASCE has no authority to enforce compliance with its standards and does not undertake to certify products for compliance or to render any professional services to any person or entity.

ASCE disclaims any and all liability for any personal injury, property damage, financial loss, or other damages of any nature whatsoever, including without limitation any direct, indirect, special, exemplary, or consequential damages, resulting from any person's use of, or reliance on, this standard. Any individual who relies on this standard assumes full responsibility for such use.

ASCE and American Society of Civil Engineers—Registered in U.S. Patent and Trademark Office.

*Photocopies and permissions.* Permission to photocopy or reproduce material from ASCE publications can be requested by sending an email to [permissions@asce.org](mailto:permissions@asce.org) or by locating a title in ASCE's Civil Engineering Database (<http://cedb.asce.org>) or ASCE Library (<http://ascelibrary.org>) and using the "Permissions" link.

**Errata: Errata, if any, can be found at <http://dx.doi.org/10.1061/9780784415955>.**

Copyright © 2023 by the American Society of Civil Engineers.

All Rights Reserved.

ISBN 978-0-7844-1595-5 (soft cover)

ISBN 978-0-7844-8383-1 (PDF)

Manufactured in the United States of America.

27 26 25 24 23 1 2 3 4 5

## ASCE STANDARDS

In 2016, the Board of Direction approved revisions to the ASCE Rules for Standards Committees to govern the writing and maintenance of standards developed by ASCE. All such standards are developed by a consensus standards process managed by the ASCE Codes and Standards Committee (CSC). The consensus process includes balloting by a balanced standards committee and reviewing during a public comment period. All standards are updated or reaffirmed by the same process every five to ten years. Requests for formal interpretations shall be processed in accordance with Section 7 of ASCE Rules for Standards Committees which are available at [www.asce.org](http://www.asce.org). Errata, addenda, supplements, and interpretations, if any, for this standard can also be found at [www.asce.org](http://www.asce.org).

This standard has been prepared in accordance with recognized engineering principles and should not be used without the user's competent knowledge for a given application. The publication of this standard by ASCE is not intended to warrant that the information contained therein is suitable for any general or specific use, and ASCE takes no position respecting the validity of patent rights. The user is advised that the determination of patent rights or risk of infringement is entirely their own responsibility.

A complete list of currently available standards is available in the ASCE Library (<https://ascelibrary.org/page/books/s-standards>).

This page intentionally left blank

# CONTENTS

PREFACE . . . . .	xiii
ACKNOWLEDGMENTS . . . . .	xv
1 GENERAL PROVISIONS . . . . .	1
1.1 Scope, Applicability, and Definitions . . . . .	1
1.1.1 Scope . . . . .	1
1.1.2 Applicability . . . . .	1
1.1.3 Definitions . . . . .	1
1.1.4 Units of Symbols and Terms . . . . .	4
1.2 Reference Specifications and Standards . . . . .	4
1.3 Material . . . . .	5
1.3.1 Standards and Codes for Specifying Stainless Steels . . . . .	5
1.3.1.1 Applicable Stainless Steel Alloys . . . . .	5
1.3.1.2 Applicable Standards for Stainless Steel Sheet and Strip . . . . .	5
1.3.1.3 Finish . . . . .	5
1.3.1.4 Welding . . . . .	5
1.3.1.5 Mechanical Assemblies . . . . .	5
1.3.2 Other Stainless Steels . . . . .	5
1.3.2.1 Ductility . . . . .	6
1.3.3 Cleaning, Descaling, and Passivation . . . . .	6
1.3.4 Corrosion Performance . . . . .	6
1.3.4.1 Service Environment Assessment . . . . .	6
1.3.4.2 Minimum Specification Requirements to Avoid Corrosion Failure . . . . .	6
1.3.4.2.1 Galvanic Corrosion . . . . .	6
1.3.4.2.2 Chloride Stress Corrosion Cracking . . . . .	6
1.3.4.2.3 Crevice Corrosion . . . . .	6
1.3.4.2.4 Salt or Brackish Water Immersion . . . . .	7
1.3.5 Yield Stress and Strength Increase from Cold Work of Forming . . . . .	7
1.3.5.1 Yield Stress . . . . .	7
1.3.5.2 Strength Increase from Cold Work of Forming . . . . .	7
2 DESIGN REQUIREMENTS . . . . .	9
2.1 General Provisions . . . . .	9
2.2 Loads and Load Combinations . . . . .	9
2.3 Design Basis . . . . .	9
2.3.1 Required Strength . . . . .	9
2.3.2 Design for Strength . . . . .	9
2.3.2.1 Allowable Strength Design Requirements . . . . .	9
2.3.2.2 Load and Resistance Factor Design Requirements . . . . .	9
2.3.3 Design for Structural Members . . . . .	9
2.3.4 Design for Connections . . . . .	9
2.3.4.1 Design for Anchorage to Concrete . . . . .	9
2.3.5 Design for Stability . . . . .	9
2.3.6 Design for Serviceability . . . . .	10
2.3.7 Design for Fatigue . . . . .	10
2.3.8 Design for Corrosion Effects . . . . .	10
2.4 Dimensional Limits and Considerations . . . . .	10
2.4.1 Limitations for Use of the Effective Width Method or the Direct Strength Method . . . . .	10
2.4.2 Members Falling Outside of the Applicability Limits . . . . .	10
2.5 Member Properties . . . . .	11
2.6 Material Properties . . . . .	11
2.7 Quality Control and Quality Assurance . . . . .	11
2.7.1 Delivered Minimum Thickness . . . . .	11

3	DESIGN FOR STABILITY . . . . .	13
3.1	Design for System Stability . . . . .	13
3.1.1	Direct Analysis Method Using Rigorous Second-Order Elastic Analysis . . . . .	13
3.1.1.1	Determination of Required Strengths . . . . .	13
3.1.1.1.1	Analysis . . . . .	13
3.1.1.1.2	Consideration of Initial Imperfections. . . . .	13
3.1.1.1.3	Modification of Section Stiffness . . . . .	14
3.1.1.2	Determination of Available Strengths . . . . .	14
3.1.2	Direct Analysis Method Using Amplified First-Order Elastic Analysis . . . . .	14
3.1.2.1	Determination of Required Strengths . . . . .	14
3.1.2.1.1	Analysis . . . . .	14
3.1.2.1.2	Consideration of Initial Imperfections. . . . .	15
3.1.2.1.3	Modification of Section Stiffness . . . . .	15
3.1.2.2	Determination of Available Strengths . . . . .	15
3.1.3	Effective Length Method . . . . .	15
3.1.3.1	Determination of Required Strengths . . . . .	15
3.1.3.1.1	Analysis . . . . .	15
3.1.3.1.2	Consideration of Initial Imperfections. . . . .	15
3.1.3.2	Determination of Available Strengths . . . . .	15
3.2	Member Bracing . . . . .	16
3.2.1	Bracing of Axially Loaded Compression Members. . . . .	16
3.2.2	Bracing of Flexural Members . . . . .	16
3.2.2.1	Neither Flange Connected to Sheathing that Contributes to the Strength and Stability of the C- or Z-Section . . . . .	16
4	MEMBERS IN TENSION . . . . .	19
4.1	General Requirements . . . . .	19
4.2	Yielding of Gross Section . . . . .	19
4.2.1	Initiation of Yielding. . . . .	19
4.2.2	Inelastic Reserve Strength . . . . .	19
4.3	Rupture of Net Section . . . . .	19
5	MEMBERS IN COMPRESSION . . . . .	21
5.1	General Requirements . . . . .	21
5.2	Yielding and Global (Flexural, Flexural-Torsional, and Torsional) Buckling . . . . .	21
5.2.1	Sections Not Subject to Torsional or Flexural-Torsional Buckling. . . . .	21
5.2.2	Singly Symmetric Sections Subject to Flexural-Torsional Buckling . . . . .	21
5.2.3	Doubly or Point Symmetric Sections . . . . .	22
5.2.4	Nonsymmetric Sections . . . . .	22
5.3	Local Buckling Interacting with Yielding and Global Buckling . . . . .	22
5.3.1	Effective Width Method . . . . .	22
5.3.1.1	Members without Holes . . . . .	22
5.3.1.2	Members with Holes. . . . .	22
5.3.2	Direct Strength Method . . . . .	22
5.3.2.1	Members without Holes . . . . .	22
5.3.2.2	Members with Holes. . . . .	22
5.3.3	Closed Cylindrical Tubular Sections . . . . .	23
5.4	Distortional Buckling . . . . .	23
5.4.1	Members without Holes . . . . .	23
5.4.2	Members with Holes. . . . .	23
6	MEMBERS IN FLEXURE . . . . .	25
6.1	General Requirements . . . . .	25
6.2	Yielding and Global (Lateral-Torsional) Buckling . . . . .	25
6.2.1	Initiation of Yielding and Global Buckling Strength . . . . .	25
6.2.1.1	Open Sections Bending About Symmetric Axis . . . . .	25
6.2.1.2	Open Sections Bending About Nonsymmetric Principal Axis . . . . .	26
6.2.1.3	Open Point Symmetric Sections . . . . .	26
6.2.1.4	Closed Box Sections . . . . .	26
6.2.1.5	Closed Cylindrical Tubular Sections . . . . .	26

6.2.2	Inelastic Reserve Strength . . . . .	27
6.3	Local Buckling Interacting with Yielding and Global Buckling . . . . .	27
6.3.1	Effective Width Method . . . . .	27
	6.3.1.1 Members without Holes . . . . .	27
	6.3.1.2 Members with Holes . . . . .	27
6.3.2	Direct Strength Method . . . . .	27
	6.3.2.1 Members without Holes . . . . .	27
	6.3.2.2 Members with Holes . . . . .	27
	6.3.2.3 Members Considering Local Inelastic Reserve Strength . . . . .	27
6.3.3	Closed Cylindrical Tubular Sections . . . . .	28
6.4	Distortional Buckling . . . . .	28
	6.4.1 Members without Holes . . . . .	28
	6.4.2 Members with Holes . . . . .	29
	6.4.3 Members Considering Distortional Inelastic Reserve Strength . . . . .	29
7	MEMBERS IN SHEAR AND WEB CRIPPLING . . . . .	31
7.1	General Requirements . . . . .	31
7.2	Shear Strength of Webs without Holes . . . . .	31
	7.2.1 Flexural Members without Transverse Web Stiffeners . . . . .	31
	7.2.2 Flexural Members with Transverse Web Stiffeners . . . . .	31
	7.2.3 Web Elastic Shear Buckling Force, $V_{cr}$ . . . . .	32
7.3	Shear Strength of C-Section Webs with Holes . . . . .	32
7.4	Transverse Web Stiffeners . . . . .	32
	7.4.1 Conforming Transverse Web Stiffeners . . . . .	32
	7.4.2 Nonconforming Transverse Web Stiffeners . . . . .	32
7.5	Web Crippling Strength of Webs without Holes . . . . .	32
7.6	Web Crippling Strength of C-Section Webs with Holes . . . . .	33
7.7	Bearing Stiffeners . . . . .	35
	7.7.1 Compact Bearing Stiffeners . . . . .	35
	7.7.2 Stud and Track Type Bearing Stiffeners in C-Section Flexural Members . . . . .	36
	7.7.3 Nonconforming Stiffeners . . . . .	36
8	MEMBERS UNDER COMBINED FORCES . . . . .	37
8.1	Combined Axial Load and Bending . . . . .	37
	8.1.1 Combined Tensile Axial Load and Bending . . . . .	37
	8.1.2 Combined Compressive Axial Load and Bending . . . . .	37
8.2	Combined Bending and Shear . . . . .	37
8.3	Combined Bending and Web Crippling . . . . .	38
8.4	Combined Bending and Torsional Loading . . . . .	39
9	ASSEMBLIES AND SYSTEMS . . . . .	41
9.1	Built-Up Sections . . . . .	41
	9.1.1 Flexural Members Composed of Two Back-to-Back C-Sections . . . . .	41
	9.1.2 Compression Members Composed of Two Sections in Contact . . . . .	41
	9.1.3 Spacing of Connections in Cover-Plated Sections . . . . .	41
9.2	Systems with Mixed Materials . . . . .	42
10	CONNECTIONS AND JOINTS . . . . .	43
10.1	General Provisions . . . . .	43
10.2	Welded Connections . . . . .	43
	10.2.1 Groove Welds in Butt Joints . . . . .	43
	10.2.2 Arc Spot Welds . . . . .	43
	10.2.2.1 Minimum Edge and End Distance . . . . .	44
	10.2.2.2 Shear . . . . .	44
	10.2.2.2.1 Shear Strength for Sheet(s) Welded to a Thicker Supporting Member . . . . .	44
	10.2.2.2.2 Shear Strength for Sheet-to-Sheet Connections . . . . .	45
	10.2.2.3 Tension . . . . .	45
	10.2.2.4 Combined Shear and Tension on an Arc Spot Weld . . . . .	46
	10.2.3 Arc Seam Welds . . . . .	46
	10.2.3.1 Minimum Edge and End Distance . . . . .	46

	10.2.3.2	Shear . . . . .	46
	10.2.3.2.1	Shear Strength for Sheet(s) Welded to a Thicker Supporting Member . . . . .	46
	10.2.3.2.2	Shear Strength for Sheet-to-Sheet Connections. . . . .	47
	10.2.4	Top Arc Seam Sidelap Welds . . . . .	47
	10.2.4.1	Shear Strength of Top Arc Seam Sidelap Welds . . . . .	47
	10.2.5	Fillet Welds . . . . .	47
	10.2.6	Flare Groove Welds . . . . .	48
	10.2.7	Resistance Welds. . . . .	50
10.3		Bolted Connections . . . . .	50
	10.3.1	Minimum Spacing . . . . .	51
	10.3.2	Minimum Edge and End Distances . . . . .	51
	10.3.3	Bearing . . . . .	51
	10.3.3.1	Bearing Strength without Consideration of Bolt Hole Deformation . . . . .	52
	10.3.3.2	Bearing Strength with Consideration of Bolt Hole Deformation . . . . .	52
	10.3.4	Shear and Tension in Stainless Steel Bolts . . . . .	52
10.4		Screw Connections. . . . .	53
	10.4.1	Minimum Spacing . . . . .	53
	10.4.2	Minimum Edge and End Distances . . . . .	53
	10.4.3	Shear . . . . .	53
	10.4.3.1	Shear Strength Limited by Tilting and Bearing. . . . .	54
	10.4.3.2	Shear in Screws . . . . .	54
	10.4.4	Tension. . . . .	54
	10.4.4.1	Pull-Out Strength. . . . .	54
	10.4.4.2	Pull-Over Strength . . . . .	54
	10.4.4.3	Tension in Screws . . . . .	54
	10.4.5	Combined Shear and Tension . . . . .	54
	10.4.5.1	Combined Shear and Pull-Over . . . . .	54
	10.4.5.2	Combined Shear and Pull-Out . . . . .	54
	10.4.5.3	Combined Shear and Tension in Screws . . . . .	55
10.5		Rupture . . . . .	56
	10.5.1	Shear Rupture . . . . .	56
	10.5.2	Tension Rupture . . . . .	57
	10.5.3	Block Shear Rupture. . . . .	57
11		STRENGTH FOR SPECIAL CASES . . . . .	59
	11.1	Test Standards . . . . .	59
	11.2	Tests for Special Cases . . . . .	59
	11.2.1	Tests for Determining Structural Performance . . . . .	59
	11.2.1.1	Load and Resistance Factor Design and Limit States Design . . . . .	59
	11.2.1.2	Allowable Strength Design . . . . .	61
	11.2.2	Tests for Confirming Structural Performance . . . . .	61
	11.2.3	Tests for Determining Mechanical Properties . . . . .	61
	11.2.3.1	Full Section. . . . .	61
	11.2.3.2	Flat Elements of Formed Sections. . . . .	61
	11.2.3.3	Virgin Stainless Steel . . . . .	61
	11.2.3.4	Determination of Stress-Strain Relationships . . . . .	61
12		DESIGN FOR SERVICEABILITY . . . . .	63
	12.1	Serviceability Determination for the Effective Width Method . . . . .	63
	12.2	Serviceability Determination for the Direct Strength Method. . . . .	63
	12.3	Flange Curling . . . . .	63
	12.4	Section Distortion . . . . .	63
	12.4.1	Local Buckling. . . . .	63
	12.4.2	Distortional Buckling . . . . .	63
13		DESIGN FOR FATIGUE . . . . .	65
	13.1	General . . . . .	65
	13.2	Calculation of Maximum Stresses and Stress Ranges. . . . .	65
	13.3	Design Stress Range . . . . .	65
	13.4	Bolts and Threaded Parts . . . . .	66
	13.5	Special Fabrication Requirements . . . . .	67

APPENDIX A	EFFECTIVE WIDTH OF ELEMENTS . . . . .	69
A1	Effective Width of Stiffened Elements . . . . .	69
	A1.1 Uniformly Compressed Stiffened Elements with Circular or Noncircular Holes. . . . .	70
	A1.2 Webs and Other Stiffened Elements Under Stress Gradient . . . . .	70
	A1.3 C-Section Webs with Holes Under Stress Gradient. . . . .	71
	A1.4 Uniformly Compressed Elements Restrained by Intermittent Connections. . . . .	71
A2	Effective Width of Unstiffened Elements . . . . .	73
	A2.1 Uniformly Compressed Unstiffened Elements . . . . .	73
	A2.2 Unstiffened Elements and Edge Stiffeners with Stress Gradient . . . . .	73
A3	Effective Width of Uniformly Compressed Elements with a Simple Lip Edge Stiffener . . . . .	75
A4	Effective Width of Stiffened Elements with Single or Multiple Intermediate Stiffeners or Edge-Stiffened Elements with Intermediate Stiffener(s). . . . .	76
	A4.1 Effective Width of Uniformly Compressed Stiffened Elements with Single or Multiple Intermediate Stiffeners . . . . .	76
	A4.1.1 Specific Case: Single or n Identical Stiffeners, Equally Spaced . . . . .	76
	A4.1.2 General Case: Arbitrary Stiffener Size, Location, and Number. . . . .	77
	A4.2 Edge-Stiffened Elements with Intermediate Stiffener(s) . . . . .	77
APPENDIX B	ELASTIC BUCKLING ANALYSIS OF MEMBERS. . . . .	79
B1	General Provisions . . . . .	79
B2	Numerical Solutions . . . . .	79
B3	Analytical Solutions . . . . .	80
	B3.1 Members Subject to Compression. . . . .	80
	B3.1.1 Global Buckling ( $F_{cre}$ , $P_{cre}$ ) . . . . .	80
	B3.1.2 Local Buckling ( $F_{crt}$ , $P_{crt}$ ) . . . . .	80
	B3.1.3 Distortional Buckling ( $F_{crd}$ , $P_{crd}$ ) . . . . .	80
	B3.2 Members with Holes Subject to Compression . . . . .	81
	B3.2.1 Global Buckling ( $F_{cre}$ , $P_{cre}$ ) for Members with Holes . . . . .	81
	B3.2.1.1 Sections with Holes Not Subject to Torsional or Flexural-Torsional Buckling. . . . .	81
	B3.2.1.2 Singly Symmetric Sections (with Holes) Subject to Flexural-Torsional Buckling. . . . .	81
	B3.2.1.3 Doubly Symmetric or Point Symmetric Sections with Holes . . . . .	82
	B3.2.1.4 Nonsymmetric Sections with Holes. . . . .	82
	B3.2.2 Local Buckling ( $F_{crt}$ , $P_{crt}$ ) for Members with Holes . . . . .	83
	B3.2.3 Distortional Buckling ( $F_{crd}$ , $P_{crd}$ ) for Members with Holes. . . . .	83
	B3.3 Members Subject to Flexure. . . . .	84
	B3.3.1 Global Buckling ( $F_{cre}$ , $M_{cre}$ ). . . . .	84
	B3.3.2 Local Buckling ( $F_{crt}$ , $M_{crt}$ ) . . . . .	84
	B3.3.3 Distortional Buckling ( $F_{crd}$ , $M_{crd}$ ) . . . . .	84
	B3.4 Members with Holes Subject to Flexure . . . . .	84
	B3.4.1 Global Buckling ( $F_{cre}$ , $M_{cre}$ ) for Members with Holes . . . . .	84
	B3.4.1.1 Open Sections (with Holes) Bending About Symmetric Axis . . . . .	85
	B3.4.1.2 Open Point Symmetric Sections with Holes . . . . .	85
	B3.4.1.3 Closed Box Section with Holes. . . . .	85
	B3.4.2 Local Buckling ( $F_{crt}$ , $M_{crt}$ ) for Members with Holes. . . . .	85
	B3.4.3 Distortional Buckling ( $F_{crd}$ , $M_{crd}$ ) for Members with Holes . . . . .	85
	B3.5 Shear Buckling ( $V_{cr}$ ). . . . .	85
APPENDIX C	MATERIAL PROPERTIES . . . . .	87
C1	Mechanical properties . . . . .	87
C2	Material Behavior . . . . .	87
	C2.1 Stress-Strain Behavior . . . . .	87
	C2.2 Tangent Modulus. . . . .	89
	C2.3 Secant Modulus . . . . .	89
	C2.4 Effective Proportional Limit-to-Yield Strength . . . . .	89
C1	GENERAL PROVISIONS. . . . .	91
	C1.1 Scope, Applicability, and Definitions . . . . .	91
	C1.1.1 Scope. . . . .	91

	C1.1.2	Applicability . . . . .	91
	C1.1.3	Definitions . . . . .	91
	C1.1.4	Units of Symbols and Terms . . . . .	91
C1.2		Reference Codes and Standards . . . . .	91
C1.3		Material. . . . .	91
	C1.3.1.4	Welding . . . . .	92
	C1.3.1.5	Mechanical Assemblies . . . . .	92
	C1.3.2	Other Stainless Steels . . . . .	92
	C1.3.2.1	Ductility . . . . .	92
	C1.3.3	Cleaning, Descaling, and Passivation . . . . .	92
	C1.3.4	Corrosion Performance. . . . .	92
	C1.3.4.1	Service Environment Assessment . . . . .	92
	C1.3.4.2	Minimum Specification Requirements to Avoid Corrosion Failure. . . . .	92
	C1.3.4.2.1	Galvanic Corrosion . . . . .	92
	C1.3.4.2.2	Chloride Stress Corrosion Cracking. . . . .	93
	C1.3.4.2.3	Crevice Corrosion . . . . .	93
	C1.3.4.2.4	Salt or Brackish Water Immersion . . . . .	93
	C1.3.5	Yield Stress and Strength Increase from Cold Work of Forming . . . . .	93
	C1.3.5.1	Yield Stress. . . . .	93
	C1.3.5.2	Strength Increase from Cold Work of Forming. . . . .	94
C2		DESIGN REQUIREMENTS . . . . .	95
	C2.1	General Provisions . . . . .	95
	C2.2	Loads and Load Combinations . . . . .	95
	C2.3	Design Basis . . . . .	95
	C2.3.1	Required Strength . . . . .	95
	C2.3.2	Design for Strength . . . . .	95
	C2.3.3	Design for Structural Members . . . . .	95
	C2.3.4	Design for Connections . . . . .	95
	C2.3.5	Design for Stability . . . . .	95
	C2.3.6	Design for Serviceability. . . . .	95
	C2.3.7	Design for Fatigue . . . . .	97
	C2.3.8	Design for Corrosion Effects . . . . .	97
	C2.4	Dimensional Limits and Considerations. . . . .	97
	C2.4.1	Limitations for Use of the Effective Width Method or the Direct Strength Method . . . . .	97
	C2.4.2	Members Falling Outside the Applicability Limits . . . . .	97
	C2.5	Member Properties . . . . .	97
	C2.6	Material Properties . . . . .	97
	C2.7	Quality Control and Quality Assurance . . . . .	97
	C2.7.1	Delivered Minimum Thickness . . . . .	97
C3		DESIGN FOR STABILITY . . . . .	99
	C3.1	Design for System Stability . . . . .	99
	C3.1.1.1.2	Consideration of Initial Imperfections. . . . .	99
	C3.1.1.1.3	Modification of Section Stiffness . . . . .	99
C4		MEMBERS IN TENSION . . . . .	101
C5		MEMBERS IN COMPRESSION . . . . .	103
	C5.2	Yielding and Global (Flexural, Flexural-Torsional, and Torsional) Buckling . . . . .	103
	C5.3	Local Buckling Interacting With Yielding and Global Buckling . . . . .	103
	C5.3.1	Effective Width Method . . . . .	103
	C5.3.2	Direct Strength Method . . . . .	104
	C5.3.3	Closed Cylindrical Tubular Sections . . . . .	104
	C5.4	Distortional Buckling . . . . .	104
C6		MEMBERS IN FLEXURE . . . . .	105
	C6.2	Yielding and Global (Lateral-Torsional) Buckling . . . . .	105
	C6.2.1	Initiation of Yielding and Global Buckling Strength . . . . .	105

	C6.2.1.4	Closed Box Sections . . . . .	105
	C6.2.1.5	Closed Cylindrical Tubular Sections . . . . .	105
	C6.2.2	Inelastic Reserve Strength . . . . .	105
C6.3		Local Buckling Interacting With Yielding and Global Buckling . . . . .	105
	C6.3.1	Effective Width Method . . . . .	105
	C6.3.2	Direct Strength Method . . . . .	105
	C6.3.2.3	Members Considering Local Inelastic Reserve Strength . . . . .	105
	C6.3.3	Closed Cylindrical Tubular Sections . . . . .	106
C6.4		Distortional Buckling . . . . .	106
C7		MEMBERS IN SHEAR AND WEB CRIPPLING . . . . .	107
	C7.2	Shear Strength of Webs Without Holes . . . . .	107
	C7.2.1	Flexural Members without Transverse Web Stiffeners . . . . .	107
	C7.2.2	Flexural Members with Transverse Web Stiffeners . . . . .	107
	C7.3	Shear Strength of C-Section Webs With Holes . . . . .	107
	C7.4	Transverse Web Stiffeners . . . . .	107
	C7.4.1	Conforming Transverse Web Stiffeners . . . . .	107
	C7.5	Web Crippling Strength of Webs Without Holes . . . . .	107
	C7.6	Web Crippling Strength of C-Section Webs With Holes . . . . .	108
	C7.7	Bearing Stiffeners . . . . .	108
C8		MEMBERS UNDER COMBINED FORCES . . . . .	109
	C8.1	Combined Axial Load and Bending . . . . .	109
	C8.2	Combined Bending and Shear . . . . .	109
	C8.3	Combined Bending and Web Crippling . . . . .	109
	C8.4	Combined Bending and Torsional Loading . . . . .	109
C9		ASSEMBLIES AND SYSTEMS . . . . .	111
	C9.1	Built-Up Sections . . . . .	111
	C9.1.1	Flexural Members Composed of Two Back-to-Back C-Sections . . . . .	111
	C9.1.2	Compression Members Composed of Two Sections in Contact . . . . .	111
	C9.1.3	Spacing of Connections in Cover-Plated Sections . . . . .	111
	C9.2	Systems with Mixed Materials . . . . .	111
C10		CONNECTIONS AND JOINTS . . . . .	113
	C10.2	Welded Connections . . . . .	113
	C10.2.1	Groove Welds in Butt Joints . . . . .	114
	C10.2.2	Arc Spot Welds . . . . .	114
	C10.2.2.2	Shear . . . . .	114
	C10.2.2.2.1	Shear Strength for Sheet(s) Welded to a Thicker Supporting Member . . . . .	114
	C10.2.2.2.2	Shear Strength for Sheet-to-Sheet Connections . . . . .	114
	C10.2.2.3	Tension . . . . .	114
	C10.2.2.4	Combined Shear and Tension on an Arc Spot Weld . . . . .	114
	C10.2.3	Arc Seam Welds . . . . .	114
	C10.2.3.2.1	Shear Strength for Sheet(s) Welded to a Thicker Supporting Member . . . . .	114
	C10.2.3.2.2	Shear Strength for Sheet-to-Sheet Connections . . . . .	114
	C10.2.4	Top Arc Seam Sidelap Welds . . . . .	114
	C10.2.4.1	Shear Strength of Top Arc Seam Sidelap Welds . . . . .	114
	C10.2.5	Fillet Welds . . . . .	114
	C10.2.6	Flare Groove Welds . . . . .	114
	C10.2.7	Resistance Welds . . . . .	114
	C10.3	Bolted Connections . . . . .	114
	C10.3.3	Bearing . . . . .	115
	C10.3.3.1	Bearing Strength without Consideration of Bolt Hole Deformation . . . . .	115
	C10.3.3.2	Bearing Strength with Consideration of Bolt Hole Deformation . . . . .	115
	C10.3.4	Shear and Tension in Stainless Steel Bolts . . . . .	115
	C10.4	Screw Connections . . . . .	115
	C10.5	Rupture . . . . .	118

C11	STRENGTH FOR SPECIAL CASES . . . . .	119
C11.1	Test Standards . . . . .	119
C11.2	Tests for Special Cases . . . . .	119
C11.2.1.1	Load and Resistance Factor Design and Limit States Design . . . . .	119
C11.2.1.2	Allowable Strength Design . . . . .	119
C11.2.2	Tests for Confirming Structural Performance . . . . .	119
C11.2.3	Tests for Determining Mechanical Properties . . . . .	119
C12	DESIGN FOR SERVICEABILITY . . . . .	121
C12.1	Serviceability Determination for the Effective Width Method . . . . .	121
C12.2	Serviceability Determination for the Direct Strength Method. . . . .	121
C12.3	Flange Curling . . . . .	121
C12.4	Section Distortion . . . . .	121
C13	DESIGN FOR FATIGUE . . . . .	123
C13.1	General . . . . .	123
C13.4	Bolts and Threaded Parts . . . . .	123
C13.5	Special Fabrication Requirements . . . . .	123
	APPENDIX CA EFFECTIVE WIDTH OF ELEMENTS . . . . .	125
	APPENDIX CB ELASTIC BUCKLING ANALYSIS OF MEMBERS. . . . .	127
	APPENDIX CC MATERIAL PROPERTIES . . . . .	129
CC1	Mechanical properties . . . . .	129
CC2	Material Behavior . . . . .	129
	REFERENCES . . . . .	131
	INDEX. . . . .	135

## PREFACE

This standard provides an update to ASCE 8-02 to align the design of cold-formed stainless steel structures with the latest findings in stainless steel research and practice and, where appropriate, carbon steel research and practice. This version is a significant update from ASCE 8-02 and reflects greater maturity and adoption of cold-formed stainless steel structures worldwide in both applications and standards. Major changes from ASCE 8-02 include adoption of format and provisions aligned with American Iron and Steel Institute standard AISI S100-16 wherever possible; adoption of reliability indices aligned with AISI S100-16; adoption of the use of initial modulus of elasticity,  $E$ , and transverse 0.2% offset stress,  $F_y$ , wherever possible; and integration of new design methods such as the direct strength method and the continuous strength method.

In the United States, hot-rolled stainless steel structural members that typically have no reductions from cross-section buckling (due to the common use of thicker steel) do not have an approved standard. However, the American Institute of Steel Construction (AISC) provided a prestandard and significant design guidance in AISC Design Guide 27 (2013). As of this writing, AISC is developing a formal standard for structural stainless steel and intends to publish AISC 370 and an updated design guide in the fall of 2021. To the extent possible

this standard has been coordinated with AISC 370; however similar to differences between AISI S100-16 and AISC 360 (2016b) for carbon steel, this standard and AISC 370 also invariably have minor differences. Notably, the scope of stainless steel alloys is broader in this standard than the current scope of AISC 370 and the attention given to cross-section buckling and other issues related to the use of thin coil and sheet steel are also given greater attention in this standard than is expected in AISC 370.

Specifying stainless steel is more involved than carbon steel, both in terms of alloy selection and member availability. AISC Design Guide 27 (2013) provides a useful introduction to stainless steel and alloy selection that the user of this standard is encouraged to read. Appendix C of this standard provides a useful summary of stainless steel alloys and properties to which this standard is applicable. Engineers designing in stainless steel are encouraged to contact suppliers early in the process to ensure alloy and member availability. Because stainless steel is often employed for its superior corrosion resistance, special attention must be paid to alloy selection to achieve desired performance, and this standard provides requirements specific to stainless steel structures that greatly exceed those of typical carbon steel applications.

This page intentionally left blank

## ACKNOWLEDGMENTS

ASCE acknowledges the work of the Stainless Steel Specification Committee of the Codes and Standards Activities Division of the Structural Engineering Institute. This group comprises individuals from many backgrounds, including consulting, engineering, research, education, and private practice from around the world. This revision of the standard began in 2019 and incorporates information as described in the commentary.

This standard was prepared through the consensus standards process by balloting in compliance with the procedures of ASCE's Code and Standard Activities Committee. Those individuals who serve on the committee are:

Benjamin Schafer, Ph.D., P.E., M.ASCE, F.SEI, *Chair*  
Robert Glauz, P.E., M.ASCE, *Vice Chair*  
Hong Chen, Ph.D., P.E., M.ASCE, *Secretary*  
Nancy Baddoo  
Hannah Blum, Ph.D., M.ASCE  
Meihe Chen, M.ASCE  
Linfeng Chen, P.E., S.E., M.ASCE  
Shenggang Fan, Ph.D.  
Leroy Gardner, Ph.D.  
John Grubb, Ph.D.  
Alfred A. Herget, P.E.

Catherine Houska, M.ASCE  
Kara Peterman, Ph.D., M.ASCE  
Kim Rasmussen, Ph.D.  
Andrew Sarawit, Ph.D., P.E., S.E, M.ASCE  
Ganping Shu, Ph.D.  
Thomas Sputo, Ph.D., P.E., F.ASCE  
Kurt Voigt, P.E.  
Ben Young, Ph.D., F.ASCE  
Huanxin Yuan, Ph.D.  
Baofeng Zheng, Ph.D.

This page intentionally left blank

## CHAPTER 1 GENERAL PROVISIONS

This chapter addresses the scope and applicability of this standard; defines the terminology used; summarizes referenced specifications, codes, and standards; and provides requirements for materials.

### 1.1 SCOPE, APPLICABILITY, AND DEFINITIONS

**1.1.1 Scope** This standard applies to the design of structural members cold-formed to shape from annealed and cold-rolled austenitic, ferritic, and duplex stainless steel alloys produced to ASTM A240/A240M and A480/A480M and austenitic annealed or cold-worked stainless steels produced to ASTM A666 and A480/A480M in the form of sheet, strip, plate, or flat bar used for load-carrying purposes in (1) buildings and (2) structures other than buildings provided allowances are made for dynamic effects.

**1.1.2 Applicability** This standard includes design provisions for allowable strength design (ASD) and load and resistance factor design (LRFD). The nominal strength and stiffness of cold-formed stainless steel components such as elements, members, assemblies, connections, and details shall be determined in accordance with the provisions in Chapters 2 through 13, and Appendixes A through C of the standard.

Where the composition or configuration of the components is such that calculation of available strength or stiffness cannot be made in accordance with these provisions (excluding those in Chapter 11), structural performance shall be established from one of the following:

1. Available strength or stiffness by tests only. Specifically, the available strength is determined from tested nominal strength by applying the safety factors or the resistance factors evaluated in accordance with Section 11.2.1.1 Items 1 and 3, and Section 11.2.1.2;
2. Available strength by rational engineering analysis with confirmatory tests. Specifically, the available strength is determined from the calculated nominal strength by applying the safety factors or resistance factors evaluated in accordance with Section 11.2.1.1 Items 2 and 3, and Section 11.2.1.2; or
3. Available strength or stiffness by rational engineering analysis based on appropriate theory and engineering judgment. Specifically, the available strength is determined from the calculated nominal strength by applying the following safety factors or resistance factors:

For members,

$$\Omega = 2.00 \text{ (ASD)}$$
$$\phi = 0.80 \text{ (LRFD)}$$

For connections,

$$\Omega = 3.00 \text{ (ASD)}$$
$$\phi = 0.55 \text{ (LRFD)}$$

When rational engineering analysis is used in accordance with Item 2 or 3 of this section to determine the nominal strength for a limit state already provided in this standard, the safety factor shall not be less than the applicable safety factor ( $\Omega$ ), nor shall the resistance factor exceed the applicable resistance factor ( $\phi$ ) for the prescribed limit state.

**1.1.3 Definitions** In this standard, “shall” is used to express a mandatory requirement (i.e., a provision that the user is obliged to satisfy to comply with the standard), and “is permitted” is used to express an option within the limits of the standard.

The following definitions shall apply to terms used in the standard. Terms designated with \* are usually qualified by the type of load effect; for example, nominal tensile strength or available compressive strength. Terms designated with † are terms jointly established and coordinated by AISC and AISI standards development.

#### Stainless Steel Specific Terms

**Austenitic Stainless Steel:** A stainless steel alloy that is predominantly face-centered cubic in crystalline structure and hardenable only by cold working.

**Autopassivating:** The ability to form a protective passive film spontaneously on exposure to air or moisture, as long as the surface is free of exogenous surface contamination, without a special passivation treatment.

**Duplex (Austenitic-Ferritic) Stainless Steel:** A stainless-steel alloy that is a mixture of austenitic and ferritic crystalline structures, with at least one-fourth of the lesser phase, and hardenable only by cold working.

**Ferritic Stainless Steel:** A stainless steel alloy that is body-centered cubic in crystalline structure (with little, if any, tempered martensite), hardenable only by cold working, and responding to conventional heat treatment by quenching and tempering.

**Passivation:** Treatment for corrosion-resistant steel to eliminate corrodible surface impurities and provide a protective film.

**Passive Film:** The protective surface that forms on stainless steel, which protects it against corrosion.

**Plastic Moment:** Product of the strength at 0.2% offset permanent strain and the plastic section modulus.

**Specified Minimum Tensile Strength:** Tensile strength specified for a material as defined by ASTM and provided in Appendix C.

**Specified Minimum Yield Strength:** Yield strength specified for a material as defined by ASTM and provided in Appendix C.